

## AMERICAN GEM SOCIETY LABORATORIES™

AGS 104099776006 May 18, 2018 1.506 cts

Setting the Highest Standard for Diamond Grading\*

## The Platinum Light Performance Diamond Quality <sup>®</sup> Document

Shape and Style Measurements	Round Brillia 7.33 - 7.37 x 4.52 m	F		00% 8.1%		
Cut Grade	AGS Ideal	<b>0</b>	51			Thin to Slightly Thick
Light Performance	AGS Ideal				43.2	Faceted
Polish	AGS Ideal					
Symmetry	AGS Ideal	o		V	$\perp$	
			Ро	inted		
Color Grade	(H) AGS 2	.0				
	(014) 4 0 0	-		$\wedge$	$ \setminus / / $	$\rightarrow$
Clarity Grade	(SI1) AGS	5		$\backslash$	NK	
Carat Weight	1.506 c	:ts				
Comments				$\times$	$./\vee$	$\searrow$
Fluorescence: Negligible Girdle inscribed "AGS 104099776006" Additional twinning wisps and surface graining not shown				<b>Cey to Symbols</b> nning Wisp 🛹 stal O	•	
	A A A					
AGSL Computer Generated Light Performance Map for this Diamond. U.S. Patent No: 7382445, 7420657, 7372552						
Brightness Less Bright Contrast Light Leakage						
	_					
Cut Scale				1 1		
AGS 0 1 2	3 4	5 6	, 7	8	9	10
AGS     AGS     AGS       Ideal     Excellent     Very Good	AGS Good	AGS	Fair		AGS Poor	
Color Scale						
	3.5 4.0 4.5 5.0 5.5		7.5 8.0 8.5	9.0 9.5 10.	.0 To Far	cy Yellow
Colorless Near Colorless   GIA D E F G H I J	FaintNKLMN	Very Light	S T U	Light V W X	Y Z	Fancy Yellow Fancy Yellow
Clarity Scale						
AGS 0 1 2	3 4	5 6	7	8	9	10
Flawless/IF Very Very Slightly Included	Very Slightly Included	Slightly Incl	Slightly Included Included			
GIA Flawless/IF VVS1 VVS2	VS1 VS2	SII	SI2	h	12	13
THIS IS A REPRESENTATION OF THE ACTUAL DOCUMENT						
ORIGINAL						
Copyright © 1996-2013 American Gem Society Laboratories, LLC. All Rights Reserved.						